

Back Blocking Cement

A Smooth Application
Used In The Adhesion
For Back Blocking.

Specially formulated
Plaster designed to
provide extended
working time to
facilitate
Back Blocking.



Back Blocking Cement

UPA Direct
173 Arden Street
North Melbourne, Victoria 3051 AUSTRALIA
1300 UPA Direct - 1300 872 347
Ph: +61 3 9329 2165
Fax: +61 3 9329 2189

Description

UPA Back Blocking Cement is a specially formulated plaster designed to provide extended working time to facilitate back blocking.

Back blocking Cement reinforces the joint, minimising the deformation and possible cracking of finished joints which may occur due to stresses resulting from building movement.

Using UPA Back Blocking Cement to adhere back blocks on all ceiling joints is strongly recommended. UPA Back Blocking Cement is not recommended for use for any other purpose.

Applications

- Pour the required amount of water into a container. Important: Make sure container, tools and water are clean.
- Mixing ratio: approximately 2 litres of water with 3kg of plaster.
- Add UPA Back Blocking Cement in the container slowly, mixing the cement continually. Soaking for longer than 1 minute prior to mixing is not recommended.
- Do not mix longer than required, as this will shorten the setting time.
- Do not mix more UPA Back Blocking Cement than can be used in approximately 150 minutes.

Advantages

- Water Based
- Light Weight
- Easy to Sand
- High Strength
- Non Shrinking
- Exceptional Finish
- Easy to Apply
- Quick Setting